

1094 Bi-directional E-Glass Fiberglass Fabric



Overview: Woven fabrics are strong reinforcements because the fibers are bundled into yarns oriented in just two directions. The warp and fill yarns run at 0 and 90 degrees respectively. Thus, fabrics are anisotropic, or strong in only two directions.

Fabrics need to be oriented so the fiber yarns run parallel to the expected loads. If extra strength is needed in a different direction, another ply must be added at an angle to the first. The most common angles are +/- 45 degrees.

These narrow widths of fiberglass find many applications in selectively reinforcing edges and seams of molding and laminations as well as pipe winding applications. The fully seamed edges avoid the problems caused by cutting narrow strips from full width fabrics. These tapes saturate easily and in most respects are similar to a 10 oz. fabric.

Available in 1, 3, and 5 yard packages; custom cuts of 10 yards or more; and full rolls.

General Properties for Woven Fabrics:

High Tensile Strength	Glass is one of the strongest textile fibers, having greater specific tensile strength than steel wire of the same diameter, at a lower weight
Dimensional Stability	Low elongation under load, generally 3% or less. Glass fibers produce fabrics with excellent dimensional stability under various types of conditions.
High Heat Resistance	Glass fabrics have excellent dimensional stability under various types of conditions.
Fire Resistance	Composed of inorganic materials, glass fabrics are noncombustible, a natural choice where flammability is a concern.
Chemical Resistance	Like glass itself, fiberglass fabrics are highly resistant to attack by most chemicals.
Durability	Being inert, glass fabrics are unaffected by sunlight, fungus, or bacteria.
Economical	Glass fabrics are lower in cost than many other fabrics for smaller applications.

Specific Product Properties:

Style	7725
Finish	504
Weave Pattern	Twill
Yarn Description	Warp: ECG 75 1/0 Fill: ECH 25 1/0
Count (Ends x Picks) inches	54 x 18
Weight	8.75 oz/yard ²
Thickness	0.0096 inches
Break Strength	Warp Break: 193 lbs/in Fill Break: 173 lbs/in
Width	38 inchs

Weave Pattern Rankings:

	Thickness	Weight	Strength	Porosity
Plain	3	1	3	1
Twill	2	1	4	2
4-Harness Satin	3	1	4	2
8-Harness Satin	1	1	7	4
Leno	7	7	1	7
Mock Leno	6	1	2	4

This was a scale from 1 to 7, with 1 being the lowest and 7 being the highest.

Resin Compatibility:

Part Number	Polyester Resin	Vinyl Ester Resin	System 2000 Epoxy
543	X	X	X
573	X	X	X
1093	X	X	X
1094	X	X	X

An "X" means the fabric is compatible with the resin.
The compatibility is based on Fibre Glast Development's resins only.